

## Bio-filler made from rice husk

REF: RYZ-100

REF: RYZ-200

### Physical properties:

Humidity: lower 6,4%

Rice husk fiber size: under 450 microns

Apparent density: 620g/l

Pellet diameter

### Micronized solid

### Chemical composition

RHEOLOGICAL, GLUTINERS

LIGNIN

CELLULOSE

HEMICELLULOSE

Fe<sub>2</sub>O<sub>3</sub>

CaO

MgO

CO<sub>2</sub>

CaCO<sub>3</sub>

MgCO<sub>3</sub>

SiO<sub>2</sub>

AL<sub>2</sub>O<sub>3</sub>

RYZ-100

RYZ-200

12,85%

8,86%

18,75%

12,93%

30,00%

20,69%

15,00%

10,34%

0,01%

0,01%

1,45%

1,00%

1,03%

0,71%

2,26%

1,56%

3,19%

2,20%

2,37%

1,64%


12,66%

39,77%

0,42%

0,29%

## GRANULOMETRIC ANALYSIS



\* Non-contractual reference values